Amendments to Claims:

Please amend the claims as in the following listing:

1-16 (canceled)

17. (currently amended) A formulation for thermoplastic synthetic building material which is formulated for extrusion processing, comprising:
filler material of proportions of 65% - 90% of overall composition;
thermoplastic resin of proportions of 10% - 35% of overall composition; and
an extruder processing stabilizer/lubricant, wherein said extruder processing stabilizer/lubricant is a metallic stearate, and wherein said filler material, said thermoplastic resin and said extruder processing stabilizer/lubricant combine to form a thermoplastic material.

18. (canceled)

19. (previously presented) The formulation for synthetic building material of claim 17, wherein:
said extruder processing stabilizer/lubricant makes up 0.5-4.0% of the overall composition.

20. (canceled)

21. (currently amended) The formulation for synthetic building material of claim 17, wherein:
said filler material is mineral filler is chosen from a group consisting of limestone, dolomite, talc, silica and flyash.

22. (original) The formulation for synthetic building material of claim 17, wherein:
said thermoplastic resin is recycled thermoplastic resin.

23. (original) The formulation for synthetic building material of claim 17, wherein:
said thermoplastic resin is virgin thermoplastic resin.

24. (original) The formulation for synthetic building material of claim 17, wherein:
said thermoplastic resin is chosen from a group consisting of polyethylene (PE), polypropylene and poly vinyl chloride (PVC).

25. (original) The formulation for synthetic building material of claim 17, further comprising:
desiccant/ moisture absorbent.

26. (original) The formulation for synthetic building material of claim 25, wherein:
said desiccant/ moisture absorbent is a metallic oxide.

27. (original) The formulation for synthetic building material of claim 26, wherein:
said desiccant/ moisture absorbent is chosen from a group consisting of calcium oxide and magnesium oxide.

28. (original) The formulation for synthetic building material of claim 17, further comprising:
additives chosen from the group consisting of antioxidant, UV stabilizer, flame retardant, wax, and inorganic color pigments.

29. (currently amended) A synthetic thermoplastic building material formulated for commercial extrusion processing, said material comprising:
filler material of proportions of 65% - 90% of overall composition;
thermoplastic resin of proportions of 10% - 35% of overall composition; and
extruder processing stabilizer/lubricant which is ~~chosen from a group consisting of~~ metallic stearate~~, hydrocarbons, fatty acids, esters, amides fluoropolymers, silicones, and boron nitride,~~ wherein said filler material, said thermoplastic resin and said extruder processing stabilizer/lubricant combine to form a thermoplastic material.

30. (previously presented) The synthetic building material of claim 29, wherein:
said extruder processing stabilizer/lubricant makes up 0.5-4.0% of the overall composition.

31. (original) The synthetic building material of claim 29, wherein:
said filler material is mineral filler which is chosen from a group consisting of limestone, dolomite, talc, silica and flyash.

32. (original) The synthetic building material of claim 29, wherein:
said thermoplastic resin is recycled thermoplastic resin

33. (original) The synthetic building material of claim 29, wherein:
said thermoplastic resin is virgin thermoplastic resin

34. (original) The synthetic building material of claim 29, wherein:
said recycled thermoplastic resin is chosen from a group consisting of polyethylene (PE), polypropylene and poly vinyl chloride (PVC).

35. (original) The synthetic building material of claim 29, further comprising:
desiccant/ moisture absorbent which is chosen from a group consisting of calcium oxide and magnesium oxide.

36. (original) The synthetic building material of claim 29, further comprising:
additives chosen from the group consisting of antioxidant, UV stabilizer, flame retardant, wax, and inorganic color pigments.

37. (original) The synthetic building material of claim 29, wherein:
said synthetic building material is shaped into panels for roofing.

38. (original) The synthetic building material of claim 29, wherein:
said synthetic building material is shaped into panels for siding.

39. (original) The synthetic building material of claim 29, wherein:
said material is formed into pieces having the appearance of cedar shakes, including embossing a texture into surfaces.

40. (original) The synthetic building material of claim 29, wherein:
said material is formed into pieces having the appearance of cedar shingles, including embossing a texture into surfaces.

41. (original) The synthetic building material of claim 29, wherein:
said material is formed into pieces having the appearance of terra cotta tiles, including embossing a texture into surfaces.

42. (new) The formulation for synthetic building material of claim 17, wherein said metallic stearate is chosen from a group consisting of calcium stearate, zinc stearate and aluminium stearate.

43. (new) The synthetic building material of claim 29, wherein said metallic stearate is chosen from a group consisting of calcium stearate, zinc stearate and aluminium stearate.